



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification⁶ : C09G</p>	<p>A2</p>	<p>(11) International Publication Number: WO 00/00560 (43) International Publication Date: 6 January 2000 (06.01.00)</p>
<p>(21) International Application Number: PCT/US99/14558 (22) International Filing Date: 25 June 1999 (25.06.99) (30) Priority Data: 09/105,060 26 June 1998 (26.06.98) US (71) Applicant: CABOT CORPORATION [US/US]; 75 State Street, Boston, MA 02109-1806 (US). (72) Inventors: STECKENRIDER, J., Scott; 13401 Mary Lee Court, Plainfield, IL 60544 (US). MUELLER, Brian, L.; 3235 Blaine Court, Aurora, IL 60504 (US). (74) Agent: LANDO, Michelle, B.; Cabot Corporation, 157 Concord Road, Billerica, MA 01821-7001 (US).</p>		<p>(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).</p> <p>Published <i>Without international search report and to be republished upon receipt of that report.</i></p>
<p>(54) Title: CHEMICAL MECHANICAL POLISHING SLURRY AND METHOD FOR USING SAME</p> <p>(57) Abstract</p> <p>An aqueous chemical mechanical polishing slurry useful for polishing the polysilicon layer of a semiconductor wafer comprising an aqueous solution of at least one abrasive, and at least one alcoholamine. The slurry preferably has a pH of from about 9.0 to about 10.5 and it includes an optional buffering agent.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

TITLE

CHEMICAL MECHANICAL POLISHING SLURRY AND METHOD FOR USING SAME

5

BACKGROUND OF THE INVENTION

1. Field of the Invention.

10 The present invention relates to a chemical mechanical polishing slurry for semiconductor integrated circuit manufacturing and, more particularly, to improved chemical mechanical polishing slurries that are useful for polishing polycrystalline silicon (Poly-Si) and various interconnect layers, metals, and thin-films used in semiconductor integrated circuit manufacturing with especially high selectivity to
15 interlayer dielectric materials.

2. Background of the Related Art.

 A semiconductor wafer typically includes a substrate, such as a silicon or
20 gallium arsenide wafer, on which a plurality of transistors have been formed. Transistors are chemically and physically connected to the substrate by patterning regions in the substrate and layers on the substrate. The transistors and layers are separated by interlevel dielectrics (ILDs), comprised primarily of some form of silicon oxide (SiO₂). The transistors are interconnected through the use of well known
25 multilevel interconnects to form functional circuits. Typical multilevel interconnects are comprised of stacked thin-films consisting of one or more of the following materials: titanium (Ti), titanium nitride (TiN), tantalum (Ta), aluminum-copper (Al-Cu), aluminum-silicon (Al-Si), copper (Cu), tungsten (W), doped poly-silicon (Poly-Si), and various combinations thereof. In addition, transistors or groups of transistors
30 are isolated from one another, often through the use of trenches filled with an insulating material such as SiO₂, SiN₄, or Poly-Si.

The traditional technique for forming interconnects has been improved by the method disclosed in U. S. Patent No. 4,789,648 to Chow et al. which relates to a method for producing coplanar multilevel metal/insulator films on a substrate. The new technique, which has gained wide interest and produces multilevel interconnects, 5 uses chemical mechanical polishing (CMP) to planarize the surface of the metal layers or thin-films during the various stages of device fabrication.

In general CMP involves the concurrent chemical and mechanical polishing of an overlying first layer to expose the surface of a non-planar second layer on which the first layer is formed. One such process is described in U. S. Patent No. 4,789,648 10 to Beyer et al., the specification of which is incorporated herein by reference. Briefly, Beyer et al, discloses a CMP process using a polishing pad and a slurry to remove a first layer at a faster rate than a second layer until the surface of the overlying first layer of material becomes coplanar with the upper surface of the covered second layer. A more detailed explanation of chemical mechanical polishing is found in U.S. Patent 15 Nos. 4,671,851, 4,910,155 and 4,944,836, the specifications of which are incorporated herein by reference.

The composition of CMP slurries is an important factor in providing an optimal chemical mechanical polishing process. Typical polishing slurries available for CMP processes contain an abrasive such as silica or alumina in an acidic or basic 20 solution. For example, U. S. Patent No. 4,789,648 to Beyer et al. discloses a slurry formulation including alumina abrasives, an acid such as sulfuric, nitric and acetic acid and deionized water. Similarly, U. S. Patent No. 5,209,816 to Yu et al. discloses an aqueous slurry including abrasive particles and an anion which controls the rate of removal of silica.

25 Other CMP polishing slurries are described in U. S. Patent Nos. 5,354,490 to Yu et al., 5,340,370 to Cadien et al., 5,209,816 to Yu et al., 5,157,876 and 5,137,544 to Medellin, and 4,956,313 to Cote et al., the specifications of each which are incorporated herein by reference.

Although many of the slurry compositions are suitable for limited purposes, 30 the slurries described above tend to exhibit unacceptable polishing rates and corresponding selectivity levels to insulator materials used in wafer manufacture. In addition, known polishing slurries tend to produce poor film removal traits for the

underlying films or produce deleterious film-corrosion which leads to poor manufacturing yields.

Accordingly, a need remains for new and improved polishing slurries and processes having high selectivity to the insulator media surrounding the trenches or interconnects, e.g., silica, spin-on-glass, and low k dielectric material which are not hazardous or corrosive. A further need remains for a single slurry which is capable of providing both high and uniform removal rates of the first layer and high selectivities to the insulator films.

10

SUMMARY OF THE INVENTION

This invention is a chemical mechanical polishing slurry that is especially useful for polishing semi-conductive layers of a semiconductor integrated circuit at high rates.

15

This invention is also a chemical mechanical polishing slurry that exhibits a high selectivity towards polishing a dielectric layer in comparison to an interlevel dielectric layer (ILD) layer of an IC circuit.

Furthermore, this invention is a chemical mechanical polishing slurry that has good storage stability.

20

This invention is also a method for using a chemical mechanical polishing slurry to polish at least one layer of a substrate such as an integrated circuit.

In one embodiment, this invention is an aqueous chemical mechanical polishing composition for polishing a substrate containing a metal or silicon layer or thin film. The aqueous chemical mechanical polishing slurry includes at least one abrasive and at least one alcoholamine wherein the alcoholamine is preferably a tertiary alcoholamine.

25

In another embodiment, this invention is an aqueous chemical mechanical polishing slurry. The aqueous chemical mechanical polishing slurry comprises from about 0.5 to about 15 weight percent fumed silica, from about 50ppm to about 2.0 weight percent 2-dimethylamino-2-methyl-1-propanol, and from about 0.01 to about 1.0 weight percent ammonium bicarbonate buffering agent. The

30

aqueous chemical polishing slurry preferably has a pH of from about 9.0 to about 10.5 and exhibits a polysilicon to PETEOS polishing selectivity of at least 500.

DESCRIPTION OF THE CURRENT EMBODIMENT

5

The present invention is directed to chemical mechanical polishing slurries for polishing conductive and semi-conductive layers and thin-films with high selectivity to ILD materials. The polishing slurry is an aqueous medium including at least one abrasive and at least one alcoholamine. The slurry may also include optional additives such as a buffering agent.

10

The first component of the slurry of this invention is at least one abrasive. The abrasive is typically a metal oxide abrasive. The metal oxide abrasive may be selected from the group including alumina, titania, zirconia, germania, silica, ceria and mixtures thereof. The CMP slurry of this invention may include from about 0.1 to about 55 weight percent or more of an abrasive. It is more preferred, however, that the CMP slurry of this invention includes from about 0.5 to about 15 weight percent abrasive and most preferably, 0.5 to about 3.0 wt % of an abrasive.

15

The metal oxide abrasive may be produced by any techniques known to those skilled in the art. Metal oxide abrasives can be produced using any high temperature process such as sol-gel, hydrothermal or, plasma process, or by processes for manufacturing fumed or precipitated metal oxides. Preferably, the metal oxide is a fumed or precipitated abrasive and, more preferably it is a fumed abrasive such as fumed silica or fumed alumina. For example, the production of fumed metal oxides is a well-known process which involves the hydrolysis of suitable feedstock vapor (such as aluminum chloride for an alumina abrasive) in a flame of hydrogen and oxygen. Molten particles of roughly spherical shapes are formed in the combustion process, the diameters of which are varied through process parameters. These molten spheres of alumina or similar oxide, typically referred to as primary particles, fuse with one another by undergoing collisions at their contact points to form branched, three dimensional chain-like aggregates. The force necessary to break aggregates is considerable. During cooling and collecting, the aggregates undergo further collision that may result in some mechanical entanglement to form agglomerates. Agglomerates are thought to be loosely held together by van der Waals forces and can

25

30

be reversed, *i.e.*, de-agglomerated, by proper dispersion in a suitable media.

Precipitated abrasives may be manufactured by conventional techniques such as by coagulation of the desired particles from an aqueous medium under the influence of high salt concentrations, acids or other coagulants. The particles are
5 filtered, washed, dried and separated from residues of other reaction products by conventional techniques known to those skilled in the art.

A preferred metal oxide will have a surface area, as calculated from the method of S. Brunauer, P.H. Emmet, and I. Teller, J. Am. Chemical Society, Volume 60, Page 309 (1938) and commonly referred to as BET, ranging from about 5 m²/g to
10 about 430 m²/g and preferably from about 30m²/g to about 170 m²/g. Due to stringent purity requirements in the IC industry the preferred metal oxide should be of a high purity. High purity means that the total impurity content, from sources such as raw material impurities and trace processing contaminants, is typically less than 1% and preferably less than 0.01% (*i.e.*, 100 ppm).

15 The metal oxide abrasive useful in the dispersion of this invention may consist of metal oxide aggregates or individual single sphere particles. The term "particle" as it is used herein refers to both aggregates of more than one primary particle and to single particles.

It is preferred that the metal oxide abrasive consists of metal oxide particles
20 having a size distribution less than about 1.0 micron, a mean particle diameter less than about 0.4 micron and a force sufficient to repel and overcome the van der Waals forces between abrasive aggregates themselves. Such metal oxide abrasive has been found to be effective in minimizing or avoiding scratching, pit marks, divots and other surface imperfections during polishing. The particle size distribution in the present
25 invention may be determined utilizing known techniques such as transmission electron microscopy (TEM). The mean particle diameter refers to the average equivalent spherical diameter when using TEM image analysis, *i.e.*, based on the cross-sectional area of the particle. By force is meant that either the surface potential or the hydration force of the metal oxide particles must be sufficient to repel and
30 overcome the van der Waals attractive forces between the particles.

In another preferred embodiment, the metal oxide abrasive may consist of discrete, individual metal oxide particles having a primary particle diameter less than

0.4 micron (400nm) and a surface area ranging from about 10 m²/g to about 250 m²/g.

Preferably, the metal oxide abrasive is incorporated into the aqueous medium of the polishing slurry as a concentrated aqueous dispersion of metal oxides. The concentrated aqueous dispersion of metal oxides comprising from about 3% to about 5 45% solids, and preferably between 10% and 20% solids. The aqueous dispersion of metal oxides may be produced utilizing conventional techniques, such as slowly adding the metal oxide abrasive to an appropriate media, for example, deionized water, to form a colloidal dispersion. The dispersion is typically completed by subjecting it to high shear mixing conditions known to those skilled in the art. The 10 pH of the slurry may be adjusted away from the isoelectric point to maximize colloidal stability.

A most preferred abrasive of this invention is fumed silica.

The chemical mechanical polishing slurry of this invention includes at least one alcoholamine. It has been found that the addition of an alcoholamine to the 15 polishing slurry enhances the polishing rate of the polysilicon compound in comparison to the underlying ILD layer. Any alcoholamines may be used in the compositions of this invention. Examples of useful alcoholamines include ethanol amines, propanol amines, primary alcoholamines, secondary alcoholamines, tertiary alcoholamines and so forth. A most preferred type of alcoholamines useful in the 20 compositions of this invention are tertiary alcoholamines. Examples of useful tertiary alcoholamines include triethynol amine, dialkylethynol amine, alkyl diethynol amine and the like. It is preferred that the tertiary alcoholamine include two methyl groups and one isopropyl group. A most preferred tertiary alcoholamine is 2-dimethylamino-2-methyl-1-propanol.

25 The alcoholamine is present in the compositions of this invention in the amount that improves the polysilicon polishing rate. The amount of alcoholamine used in the compositions of this invention will vary from about 50 ppm to about 2 wt % or more. More preferably, the alcoholamine should be present in the composition of this invention in an amount ranging from about 500 ppm to about 1.0 wt %.

30 A buffering agent may be added to the compositions of this invention as an optional ingredient. The buffer functions in the compositions of this invention to make the slurries more resistant in pH change. In addition, the polysilicon rate is

slightly enhanced by adding a buffer to the compositions of this invention. Any buffer which possesses an acid/conjugate base with a pKa close to the desired composition pH is preferred as a composition buffer. The actual pH can be approximated with the equation:

5
$$\text{pH} = \text{pKa} + \log \frac{[\text{conjugate base}]}{[\text{acid}]}$$

which may be used in the compositions of this invention. It is preferred however that the buffer does not contain metallic ions. Especially useful buffers include carbonate and bicarbonate buffers such as ammonium bicarbonate.

10 The buffer, if used, should be present in the compositions of this invention in amounts ranging from about 0.01 to about 1.0 wt %. It is most preferred that the buffer is present in the compositions of this invention in an amount ranging from about 0.01 to about 0.15 wt %.

15 Other well known polishing slurry additives may be incorporated into the chemical mechanical polishing slurry of this invention. Useful optional additives include surfactants, stabilizers, complexing agents, film forming agents and the like compositions. An example of one class of optional additives are inorganic acids and/or salts thereof which may be added to the polishing slurry to further improve or enhance the polishing rate of the barrier layers in the wafer, such as titanium and tantalum. Useful inorganic additives include sulfuric acid, phosphoric acid, nitric acid, HF acid, ammonium fluoride, ammonium salts, potassium salts, sodium salts or
20 other cationic salts of sulfates, phosphates and fluorides.

 It is desirable to maintain the pH of the CMP slurry of this invention within a range of from about 7.0 to about 12.0, more preferably within a range of from about 8.0 to about 12.0, and most preferably within a range of from about 9.0 to about 10.5
25 in order to facilitate control of the CMP process. Substrate polishing quality problems are encountered when the pH of the CMP slurry of this invention is too low, e.g., less than about 8. The pH of the CMP slurry of this invention may be adjusted using any known acids or bases. However, the use of an acid or base that contains no metal ions, such as ammonium hydroxide or nitric, phosphoric, sulfuric, or organic acids are
30 preferred to avoid introducing undesirable metal components into the CMP slurry of this invention.

The CMP slurry of this invention may be used to polish any type of conductive layer including, for example, tungsten, aluminum, copper, titanium, tantalum, and mixtures thereof. However, the chemical mechanical polishing slurry of this invention has been found to be most useful for polishing conductive and semi-
5 conductive layers of integrated circuit wafers including, but not limited to titanium nitride, tantalum nitride, and polysilicon layers. The polysilicon layers can include both epitaxial silicon and polycrystalline silicon.

The chemical mechanical polishing slurries of this invention have high polysilicon (Poly-Si) polishing rate. In addition, the chemical mechanical polishing
10 slurries of this invention exhibits desirable low polishing rates towards the dielectric (PETEOS) insulating layer. As a result, the polishing slurries of this invention exhibit [Poly-Si]/[PETEOS] polishing selectivities of at least greater than 100, and preferably greater than about 500.

The CMP slurry of this invention may be produced using conventional
15 techniques known to those skilled in the art. Typically, the non-abrasive components such as the alcoholamine, are mixed into an aqueous medium, such as deionized or distilled water, at pre-determined concentrations under low shear conditions until such components are completely dissolved in the medium. A concentrated dispersion of the metal oxide abrasive, such as fumed silica, is added to the medium and diluted to
20 the desired loading level of abrasive in the final CMP slurry prior to slurry use.

The silica and the alcoholamines used in the compositions of this invention form a stable slurry. Therefore, the CMP slurries of the present invention will typically be supplied as one package system (abrasive and alcoholamine in a stable aqueous medium).

25 In a typical chemical mechanical polishing process that uses the CMP slurries of this invention, the substrate or wafer to be polished will be placed in direct contact with a rotating polishing pad. A carrier applies pressure against the backside of the substrate. During the polishing process, the pad and table are rotated while a downward force is maintained against the substrate back. A chemical mechanical
30 polishing slurry of this invention is applied to the pad during polishing. The slurry initiates the polishing process by reacting with the film being polished either mechanically, chemically, or both. The polishing process is facilitated by the

rotational movement of the pad relative to the substrate as slurry is provided to the wafer/pad interface. Polishing is continued in this manner until a least a portion of the desired film on the insulator is removed.

5

EXAMPLE 1

This Example investigates the effect of adding a tertiary alcoholamine to a conventional low-metals silica-based polishing slurry on polishing rates and selectivity to PETEOS.

10 A base polishing slurry including 2 wt% of Cab-O-Sil® L90 fumed silica having an average surface area of about 90 m²/g, manufactured by Cabot Corporation and water adjusted to a pH of 10.5 using ammonium hydroxide (NH₄OH) was prepared by admixing the ingredients. A second polishing slurry was made including 2 wt% of L90 fumed silica manufactured by Cabot Corporation and water adjusted to
15 a pH of 10.5 using 0.15 wt% of 2-dimethylamino-2-methyl-1-propanol which is a tertiary alcoholamine.

Both polishing slurries were used to polish Poly-Si and PETEOS 8" wafers using an IPEC 472 polisher loaded with a perforated IC1000/Suba IV pad manufactured by Rodel. The polishing conditions used were a 5.5 psi down-force, a
20 1.8 psi back-pressure, a 30 rpm platen speed, a 24 rpm carrier speed and a 140 ml/min slurry flow rate.

The polishing results are reported in Table I below.

Table I

Run	wt % Silica	Additive	pH	Poly-Si Rate Å/min	PETEOS Rate Å/min	Poly- Si/PETEOS Selectivity
1	2	NH ₄ OH	10.5	1868.4	48.0	38.92
2	2	T-AMINE	10.5	3003.4	9.36	320.9

25

The polishing results indicate that the Poly-Si polishing rate is enhanced and the PETEOS polishing rate is reduced by using a slurry including a tertiary alcoholamine.

EXAMPLE 2

This Example investigates the effect of amount and type of amine added to a conventional low-metals silica-based polishing slurry on polishing rates and selectivity to PETEOS.

A base polishing slurry was prepared including 2 wt% of L90 fumed silica having an average surface area of about 90 m²/g, manufactured by Cabot Corporation and water. Varying amounts and types of alcoholamines or ammonium salts were added to the slurry as set forth in Table II, below. The alcoholamines and ammonium salts combined with the base slurry included ammonium salts tetramethylammonium hydroxide ("TMAH"), methyltertiarybutylammonium hydroxide ("MTBAH"), and the alcoholamines 2-amino-2-methyl-1-propanol ("AMP-95") and 2-dimethylamino-2-methyl-1-propanol ("T-AMINE").

The polishing slurries were used to polish both Poly-Si and PETEOS 8" wafers using an IPEC 472 polisher loaded with a perforated IC1000/Suba IV pad manufactured by Rodel. The polishing conditions used were a 5.5 psi down-force, a 1.8 psi back-pressure, a 30 rpm platen speed, a 24 rpm carrier speed and a 140 ml/min slurry flow rate.

The polishing results are reported in Table II below.

Table II

Run	% solids	pH	Additive type	Additive ppm	Poly-Si Rate Å/min	PETEO S Rate Å/min	Selectivity Poly-Si/ PETEOS
3	2	10.5	TMAH	430	2968	10.16	292
4	2	10.5	MTBAH	875	3085	2.62	1177
5	2	10.3	AMP-95	1500	2367	2.88	822
6	2	10.5	T-AMINE	1500	2995	2.67	1122
7	2	10.6	T-AMINE	1500	2909	0.80	3636
8	2	10.0	T-AMINE	730	2716	3.17	857
9	2	10.0	T-AMINE	500	2218	1.25	1774
10	2	10.5	T-AMINE	1500	3232	2.50	1293
11	2	10.6	T-AMINE	5000	2987	4.32	692
12	2	11.2	T-AMINE	15000	2236	2.25	994
13	2	11.3	T-AMINE	25000	2056	2.35	875

The polishing results indicate that a silica slurry including alcoholamines i.e., (runs 5-13), exhibit a superior [Poly-Si]/[PETEOS] polishing selectivity in comparison to the same silica slurry including similar amounts of ammonium salts.

5

EXAMPLE 3

This Example investigates the effect of adding buffers to a polishing slurry including a fumed silica abrasive and at least one tertiary amine on polishing rates and defectivity.

10 A base polishing slurry including 2 wt% of L90 fumed silica having an average surface area of about 90 m²/g, manufactured by Cabot Corporation and water was prepared by admixing the ingredients. Varying amounts of ammonium bicarbonate and the tertiary alcoholamine, 2-dimethylamino-2-methyl-1-propanol, were added to the slurry in the amounts set forth in Table III below.

15 The polishing slurries were used to polish both Poly-Si and PETEOS 8" wafers using an IPEC 472 polisher loaded with a perforated IC 1000/Suba IV pad. The polishing conditions used were a 5.5 psi down-force, a 1.8 psi back-pressure, a 30 rpm platen speed, a 24 rpm carrier and a 140 ml/min slurry flow rate.

The polishing results are reported in Table III, below.

20

Table III

Run	T-Amine wt%	Buffer ppm	Poly Si Rates	PETEOS Rate	Poly- Si/PETEOS Selectivity
1	0.15	0	3197.83		
2	0.15	0	3231.71	2.5	1293
3	0.15	700	3526.36		
4	0.15	700	3564.93	5.12	696
5	0.5	0	2960.8		
6	0.5	0	2987.39	4.32	691
7	0.5	700	3474.3		
8	0.5	700	3467.33	4.28	810
9	1.5	0	2213.34		
10	1.5	0	2235.9	2.25	994
11	1.5	700	2367.87		
12	1.5	700	2344.33	4.25	552
13	2.5	0	2055.3		
14	2.5	0	2055.73	2.35	875

Went into pad wet for 30 min delay					
15	2.5	700	2135.48		
16	2.5	700	2131.76	3.94	541
17	0.15	0	3218.72	2.79	1154

The polishing results show that the addition of a buffering agent to the alcoholamine containing slurries of this invention enhances the slurry Poly-Si polishing rate without significantly altering the Poly-Si/PETEOS polishing selectivity.

5 While the present invention has been described by means of specific embodiments, it will be understood that modifications may be made without departing from the spirit of the invention. The scope of the invention is not to be considered as limited by the description of the invention set forth in the specification and examples, but rather as defined by the following claims.

10 What we claim is:

CLAIMS

1. An aqueous chemical mechanical polishing composition for polishing a substrate containing a metal or silicon layer or thin film, comprising:
 - 5 at least one abrasive; and
 - at least one alcoholamine.
2. The aqueous chemical mechanical polishing slurry of claim 1 wherein the slurry has a polysilicon to insulating layer polishing selectivity greater
10 than about 100.
3. The aqueous chemical mechanical polishing slurry of claim 1 having a slurry pH is from about 9 to about 10.5.
4. The aqueous chemical mechanical polishing slurry of claim 1 including
15 from
about 50ppm to about 2.0 wt% of at least one alcoholamine.
5. The aqueous chemical mechanical polishing slurry of claim 1 wherein
20 the alcoholamine is a tertiary amine.
6. The aqueous chemical mechanical polishing slurry of claim 1 wherein the alcoholamine is selected from triethanol amine, dialkylethanol amine, alkyl diethanol amine, and 2-dimethylamino-2-methyl-1-propanol.
25
7. The aqueous chemical mechanical polishing slurry of claim 1 wherein the alcoholamine is 2-dimethylamino-2-methyl-1-propanol.
8. The aqueous chemical mechanical polishing composition of claim 1,
30 wherein the abrasive is a metal oxide.

9. The aqueous chemical mechanical polishing slurry of claim 8, wherein the metal oxide abrasive is at least one compound selected from the group including alumina, titania, zirconia, germania, silica, ceria or chemical mixture of the metal oxides.

5

10. The aqueous chemical mechanical polishing slurry of claim 8, wherein the abrasive is a physical mixture of the elemental oxides of alumina, titania, zirconia, germania, silica, and ceria.

10 11. The aqueous chemical mechanical polishing slurry of claim 8, wherein the abrasive has a median particle size less than 1000 nm and a mean aggregate diameter less than about 400 nm.

12. The aqueous chemical mechanical polishing slurry of claim 1, wherein
15 the abrasive is present in the range of about 0.5% to 55% solids by weight.

13. The aqueous chemical mechanical polishing slurry of claim 1, wherein the abrasive is from about 0.5 to about 3.0 weight percent fumed silica.

20 14. The aqueous chemical mechanical polishing slurry of claim 1 including at least one buffering agent.

15. The aqueous chemical mechanical polishing slurry of claim 1 including a buffering agent selected from carbonate and bicarbonate buffering agents.

25

16. The aqueous chemical mechanical composition of claim 1 including ammonium bicarbonate.

17. The aqueous chemical mechanical polishing slurry of claim 1,
30 including from about 0.01 to about 1.0 weight percent of a buffering agent.

18. An aqueous chemical mechanical polishing slurry comprising:

from about 0.5 to about 15 weight percent fumed silica;

from about 50ppm to about 2.0 weight percent of at least one tertiary alcoholamine; and

from about 0.01 to about 1.0 weight percent of a buffering agent selected from
5 a carbonate, a bicarbonate, or mixtures thereof, wherein the slurry has a pH of from about 9.0 to about 10.5.

19. The aqueous chemical mechanical polishing slurry of claim 18 wherein the tertiary alcoholamine is 2-dimethylamino-2-methyl-t-propanol.

10 20. The aqueous chemical mechanical polishing slurry of claim 18 wherein the buffering agent is ammonium bicarbonate.

21. The aqueous chemical mechanical polishing slurry of claim 18 having a polysilicon to PETEOS polishing selectivity of at least 500.

15

22. A method for chemical-mechanical polishing of a substrate containing an first insulator layer and at least one second layer selected from at least one conductive or semi-conductive material the method comprising the steps of:

- 20 a) providing an aqueous chemical mechanical polishing slurry comprising an abrasive and a tertiary amine;
- b) applying the slurry to the substrate; and
- c) removing at least a portion of the second layer by bringing a polishing pad into contact with the substrate and moving the pad in relation to the substrate.

25

23. The aqueous chemical mechanical polishing slurry of claim 22 wherein the second layer is polysilicon and the slurry has a polysilicon to insulating layer polishing selectivity greater than about 100.

30 24. The method of claim 22, wherein the second layer is a conductive layer that is selected from tungsten, aluminum, copper, titanium and tantalum.

25. The method of claim 22 wherein the second layer is a semi-conductive layer selected from the group consisting of epitaxial silicon and polycrystalline silicon.

5 26. The method of claim 22 wherein the aqueous chemical mechanical polishing slurry includes from about 50ppm to about 2.0 wt% of at least one alcoholamine.

27. The method of claim 22 wherein the aqueous chemical mechanical
10 polishing slurry includes at least one tertiary alcoholamine.

28. The method of claim 22 wherein the aqueous chemical mechanical polishing slurry includes an alcoholamine selected from triethanol amine, diethylethanol amine, alkyl diethanol amine, and 2-dimethylamino-2-methyl-1-
15 propanol.

29. The method of claim 22 wherein the alcoholamine is 2-dimethylamino-2-methyl-1-propanol.

20 30. The method of claim 22 wherein the aqueous chemical mechanical polishing composition abrasive is a metal oxide.

31. The method of claim 22 wherein the aqueous chemical mechanical polishing slurry abrasive is present in the slurry in an amount ranging from about
25 0.5% to 55% by weight.

32. The method of claim 22 wherein the abrasive used in the aqueous chemical mechanical polishing slurry is from about 0.5 to about 3.0 weight percent fumed silica.

30

33. The method of claim 22 wherein the aqueous chemical mechanical polishing slurry includes at least one buffering agent.

34. A method for chemical-mechanical polishing of a substrate containing an insulator layer and a polysilicon layer, the method comprising the steps of:

- a) providing an aqueous chemical mechanical polishing slurry comprising
5 from about 0.5 to about 15 weight percent fumed silica, from about 50ppm to about 2.0 weight percent 2-dimethylamino-2-methyl-1-propanol, and at least one buffering agent wherein the slurry has a pH of from about 9.0 to about 10.5;
- b) applying the slurry to the substrate; and
- c) removing at least a portion of the polysilicon layer by bringing a
10 polishing pad into contact with the substrate and moving the pad in relation to the substrate.

35. The method of claim 34 wherein the buffering agent used in the aqueous chemical mechanical polishing slurry is from about 0.01 to about 1.0 weight percent ammonium bicarbonate.

15

36. The method of claim 34 wherein the polysilicon to insulating layer polishing selectivity of the slurry is greater than about 100.